

Neutraliser 502

For simple neutralisation of acid rinse water

Following the pickling of stainless steel, the rinse water is strongly acidic and contains dissolved metals including chromium and nickel. For environmental reasons, this water should be treated before discharge.

Standard applications

Avesta Neutraliser 502 is a simple way to neutralise acidic waste water and precipitate heavy metals.


Features

- Gives rapid precipitation of iron, chromium and nickel in the form of a sludge which can be sent for deposition.
- Adjusts the waste water to a pH-value of 7–10 before discharge.




Avesta Neutraliser 502 for the treatment of acid rinse water after pickling.


Instructions for use



1. Add the neutraliser to the rinse water while stirring.



2. Check the pH-value with litmus paper. Optimum precipitation of heavy metals (Cr/Ni) is achieved at pH 9.5.



3. The neutralised clear water and the remaining sludge should be sent for deposition according to local regulations.

Packaging

Avesta Neutraliser 502 is supplied in 32 kg polyethylene container.

Storage

Avesta Neutraliser 502 should be stored indoors at room temperature. Containers must be kept properly closed, in an upright position and inaccessible to unauthorized persons.

Worker safety

Protective clothing. In general, users should wear acid-resistant overalls, gloves and rubber boots. Face visor should be used and, if necessary, suitable respiratory protective devices.

Special conditions may apply from one country to another. Consult our website where updated Safety Data Sheets can be found.

Waste treatment

Empty containers (HDPE) must be cleaned and can then be recycled according to local regulations.

Other information

For more information, please visit our website: www.avestafinishing.com, where you can find Safety Data Sheets and other useful information.



Information given in this brochure may be subject to alteration without notice. Care has been taken to ensure that the contents of this publication are accurate, but voestalpine Böhler Welding Nordic AB and its subsidiary companies do not accept responsibility for errors or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and the company and its subsidiaries accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability.

voestalpine Böhler Welding Nordic AB

Lodgatan 14, SE-211 24 Malmö, Sweden

Tel: +46 (0)40 28 83 00

www.voestalpine.com/welding

voestalpine

ONE STEP AHEAD.