FONTARGEN A 2115/8 M



ISO 24373:	S Cu 6100 (CuAl7)
AWS A 5.7:	ERCuAl-A1
Material number:	2.0921

Composition, typical analysis (% w/w):

AI	Ni	Mn	Fe	Cu
8	0.5	0.2	0.2	Remainder

Characteristics / Applications:

MIG-brazing of aluminium plated and uncoated steel plates. Applications: Auto body, magnetic solenoids, air conditioning and container building. The corrosion resistance galvanized steel plates remain unaffected. Little deformation of thin steel sheets.

Suitable for joining of aluminium-bronze, high-strength brass and steel. Range of applications: Car body, ship building, heating and cooling as well as container building.

Mechanical properties of pure brazing deposit

(Min. values at room temperation	ure):
Melting range:	1030 - 1040 °C
Tensile strength:	380 - 450 N/mm²
Elongation (I=5d):	45 %
Thermal elongation:	17 • 10 ⁻⁶ /K
Hardness (Brinell):	60 - 80 HB
Electrical conductivity:	8 Sm/mm ²
Heat conductivity:	35 W/m • K
Specific gravity:	7.7 g/cm ³
Brazing process:	MIG-brazing
Shielding gas (DIN EN 439):	I 1 (Argon)
Current mode:	DC (+pole)
Availability:	Diameter (mm): 0.8/1.0/1.2
Spool type:	B300, S300, Drum
Welding position:	according to DIN EN 287

PA
PB
PC
PD
PE
PF
PG

Image: Im

13/10/JL/1

All information concerning our products, equipment and processes is based on extensive research work and application technology experience. We provide these results ontally and in writing in all conscience, this not however exempting the constance from the obligation to back our products and processes to not so one responsibility, especially fill the application and process has not been expressly approved by us in writing. The test certificates enclosed do not exempt the user from carrying out correct incompliant graded in application to accordance with Sections 377734 HoB (German contractic doub). Nameers 10 and 11 of our German Terma G Maa and Delivery have validly for any damaging everts.